



Titacon EX210

RESIN : POLYACETAL RESIN

**PRODUCT DESCRIPTION : EXTRUSION GRADE, PERMANENT ANTI-STATIC,
CARBON BLACK.**

Properties	Unit	method	Value
Color	-	-	Natural
specific gravity	g/cm ³	ISO 1183	1.48
Tensile strength	MPa	ISO	45
Tensile Elongation		527-1,2	>20
Flexural strength	MPa	ISO 178	70
Flexural modulus			1750
Charpy impact strength(notched)	kJ/m ²	ISO	7
		179/1eA	
Heat Deflection Temperature(1.8MPa)	°C	ISO 75-1,2	95
Volume resistivity	Ω•cm	IEC 60093	1×10 ⁶
Surface resistivity	Ω		1×10 ^{5~6}
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	1.6~1.8
MOLDING CONDITION	°C	Drying	100x 3Hrs
		Melt Temp.	170~200
		Mold Temp.	60~100
	%	Inject. Press.	30~70
		Inject. Velocity	20~50

*All property values shown in this data sheet are the representative values and not minimum value of this material.