



## Titalon 3300CF

RESIN : POLYAMIDE12 RESIN

PRODUCT DESCRIPTION : 30% CARBON FIBER REINFORCED, HIGH STRENGTH,  
HIGH CONDUCTIVE

Properties	Unit	method	Value
Color	-	-	Black
specific gravity	g/cm <sup>3</sup>	ISO 1183	1.15
Tensile strength	MPa	ISO	135
Tensile Elongation		527-1,2	>3
Flexural strength	MPa	ISO 178	200
Flexural modulus			12000
Charpy impact strength(notched)	kJ/m <sup>2</sup>	ISO	14
		179/1eA	
Heat Deflection Temperature(1.8MPa)	°C	ISO	160
		75-1,2	
Volume resistivity	Ω•cm	IEC 60093	1×10 <sup>3</sup>
Surface resistivity	Ω		1×10 <sup>3</sup>
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	0.2~0.3
MOLDING CONDITION	°C	Drying	80~100x 4Hrs
		Melt Temp.	200~230
		Mold Temp.	60~100
	%	Inject. Press.	30~70
		Inject. Velocity	30~60

\*All property values shown in this data sheet are the representative values and not minimum value of this material.