

Titalon 5030AS

樹 酯 Resin : Polycarbonate resin (PC)

產品說明 Product description : 永久抗靜電、可染色

Permanent Ant-Static

| 項目 Properties | 單位 Unit | 測試方法 Method | 數值 Value |
|--|-------------------|---------------------|----------------------|
| 顏色 Color | - | - | Natural |
| 比重 Specific gravity | g/cm ³ | ISO 1183 | 1.20 |
| 拉伸強度 Tensile strength | MPa | ISO | 50 |
| 拉伸率 Tensile Elongation | | 527-1,2 | 30 |
| 彎曲強度 Flexural strength | MPa | ISO 178 | 70 |
| 彎曲模數 Flexural modulus | | | 2000 |
| 衝擊強度(有缺口) Charpy impact strength(notched) | kJ/m ² | ISO 179/1eA | 19 |
| 熱變形溫度(1.8MPa) Heat Deflection Temperature(1.8MPa) | °C | ISO 75-1,2 | 90 |
| 體積阻抗 Volume resistivity | Ω•cm | IEC 60093 | 1×10 ⁹⁻¹¹ |
| 表面阻抗 Surface resistivity | Ω | | 1×10 ⁹⁻¹¹ |
| 耐燃性 Flammability | | UL 94 | HB |
| 模收縮 Mold shrinkage | % | 50x70x3 mmt | 0.9~1.2 |
| 成型條件 Molding condition | °C | 乾燥條件 Drying | 90-120 x 4Hrs |
| | | 料管溫度 Melt temp. | 240~280 |
| | | 模具溫度 Mold temp. | 80~130 |
| | % | 射出壓力 Inject. press. | 30~70 |
| 射出速度 Inject. velocity | | 20~50 | |

*以上數值為材料的代表性測試值、並非該規格材料的最低值。

*All property values shown in this data sheet are the representative values and not minimum value of this material.